



TECHNICAL DATA-SHEET

ALLOY DESCRIPTION: EN AB ed AC 42300 - AlSi7(Mg)

ALLOY GROUP: Al Si

STANDARD: UNI EN 1676 e 1706

CHEMICAL COMPOSITION %

Alloy	Elements	Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Pb	Sn	Ti	Others each	Others tot.
EN AB 42300	Min	6,5				0,10								
	Max	7,5	0,15	0,03	0,10	0,30	0,03	0,03	0,07	0,03	0,03	0,18	0,03	0,10
EN AC 42300	Min	6,5				0,10								
	Max	7,5	0,19	0,05	0,10	0,25	0,03	0,03	0,07	0,03	0,03	0,25	0,03	0,10

MECHANICAL PROPERTIES - EN 1706:2020

CASTING PROCESS	TEMPER DESIGNATIONS	TENSILE STRENGTH	YIELD STRENGTH	ELONGATION	BRINELL HARDNESS
		(Mpa)	(Mpa)	(%)	(HBW)
SAND CASTING	T6	200	140	3	60
	T6	220	160	8	70
SHELL CASTING	T64	170	110	10	55

PHYSICAL PROPERTIES - EN 1706:2020

DENSITY	2,66 Kg/dm ³	SOLIDIFICATION AND MELTING RANGES	550-625°C
FATIGUE RESISTANCE	80-110 MPA	OPTIMUM RANGE OF SAND CASTING	680-750°C
ELECTRIC CONDUCTIVITY	20-27 MS/m	OPTIMUM RANGE OF SHELL CASTING	680-750°C
THERMAL CONDUCTIVITY	160-180 W/(m K)	THERMAL EXPANSION (from 20°C to 100°C)	22·10 ⁻⁶ /K

TECHNOLOGICAL PROPERTIES - EN 1706:2020

CASTABILITY	GOOD	RESISTANCE TO HOT TEARING	EXCELLENT
WELDABILITY	GOOD	STRENGTH AT ELEVATED TEMPERATURE	MEDIUM
POLISHING	MEDIUM	PRESSURE TIGHTNESS	GOOD
MACHINABILITY	GOOD	DECORATIVE ANODIZING	SUFFICIENT
CORROSION RESISTANCE	GOOD	PROTECTIVE ANODIZING	SUFFICIENT

APPLICATIONS

Alloy used in the mechanical, aviation, naval and transport industries, thanks to its excellent mechanical characteristics.

Alloy compliant with food standard EN 601.

HEAT TREATMENTS

	SOLUBILISATION TEMPERATURE	SOLUBILISATION DURATION	WATER HARDENING TEMPERATURE	AGEING TEMPERATURE	AGEING DURATION
F RAW STATE	-	-	-	-	-
O ANNEALING	520-530 °C	6-8 hours	20 °C	-	-
T1 SELF-HARDENING	-	-	-	-	-
T4 SOLUBILISATION AND NATURAL AGEING	480-530 °C	2-16 hours	20-80 °C	15-30 °C	120 hours
T5 CONTROLLED COOLING AND ARTIFICIAL AGEING	-	-	AIR	210-230 °C	5-12 hours
T6 SOLUBILISATION AND ARTIFICIAL AGEING	480-555 °C	2-20 hours	20-80 °C	130-185 °C	2-15 hours
T64 SOLUBILISATION AND PARTIAL AGEING	520-545 °C	4-10 hours	20-50 °C	135-160 °C	2-7 hours
T7 HYPERAGEING	480-530 °C	1-8 hours	20 °C	190-240 °C	1-8 hours

The temperatures and the duration of the treatments vary according to the type of alloy, melting (shell, sand or die casting) and the result you want to obtain.

Ideal parameters shall be determined by a test.

EQUIVALENTS OR SIMILARS FOREIGN REGULATIONS

	ITALY	GERMANY	FRANCE	G.B.R.	USA	ISO	JAPAN	TURKEY
	UNI	Din1725/5-86	NFA57-105	BS1490-88	ASTM 179-82	3522-84	JIS H2211-92	ETIAL
Equivalents								
Similar								

What is indicated in this data sheet is limited to inform only and does not imply any guarantee regarding the properties reported.

Everything that involves decisions based on the information stated here is direct responsibility of the end user, as well as any risks, not excluded from the verification.