



TECHNICAL DATA-SHEET

ALLOY DESCRIPTION: EN AB 51200 - Al Mg 9

ALLOY GROUP: Al Mg

STANDARD: UNI EN 1676 e 1706

CHEMICAL COMPOSITION %

Alloy	Elements	Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Pb	Sn	Ti	Others each	Others tot.
EN AB 51200	Min		0,45			8,5								
	Max	2,5	0,9	0,08	0,55	10,5	0,05	0,10	0,25	0,10	0,10	0,15	0,05	0,15
EN AC 51200	Min					8,0								
	Max	2,5	1,0	0,10	0,55	10,5	0,05	0,10	0,25	0,10	0,10	0,20	0,05	0,15

MECHANICAL PROPERTIES - EN 1706:2020

CASTING PROCESS	TEMPER DESIGNATIONS	TENSILE STRENGTH	YIELD STRENGTH	ELONGATION	BRINELL HARDNESS
		(Mpa)	(Mpa)	(%)	(HBW)
DIE CASTING	F	200	130	1	70

PHYSICAL PROPERTIES - EN 1706:2020

DENSITY	2,63 Kg/dm ³	SOLIDIFICATION AND MELTING RANGES	520-620 °C
FATIGUE RESISTANCE	60-90 MPA	OPTIMUM RANGE OF DIE CASTING	640-680 °C
ELECTRIC CONDUCTIVITY	14-16 MS/m	THERMAL EXPANSION (from 20°C to 100°C)	24·10 ⁻⁶ /K
THERMAL CONDUCTIVITY	130-140 W/(m K)		

TECHNOLOGICAL PROPERTIES - EN 1706:2020

CASTABILITY	MEDIUM	RESISTANCE TO HOT TEARING	SUFFICIENT
WELDABILITY	POOR	STRENGTH AT ELEVATED TEMPERATURE	GOOD
POLISHING	EXCELLENT	PRESSURE TIGHTNESS	SUFFICIENT
MACHINABILITY	EXCELLENT	DECORATIVE ANODIZING	GOOD
CORROSION RESISTANCE	EXCELLENT	PROTECTIVE ANODIZING	GOOD

APPLICATIONS

Corrosion resistant alloy, mainly used in the marine, furniture and food industries.

Used in die casting. Alloy compliant with the Food standard EN 601.

HEAT TREATMENTS

	SOLUBILISATION TEMPERATURE	SOLUBILISATION DURATION	WATER HARDENING TEMPERATURE	AGEING TEMPERATURE	AGEING DURATION
F RAW STATE	-	-	-	-	-
O ANNEALING	520-530 °C	6-8 hours	20 °C	-	-
T1 SELF-HARDENING	-	-	-	-	-
T4 SOLUBILISATION AND NATURAL AGEING	480-530 °C	2-16 hours	20-80 °C	15-30 °C	120 hours
T5 CONTROLLED COOLING AND ARTIFICIAL AGEING	-	-	AIR	210-230 °C	5-12 hours
T6 SOLUBILISATION AND ARTIFICIAL AGEING	480-555 °C	2-20 hours	20-80 °C	130-185 °C	2-15 hours
T64 SOLUBILISATION AND PARTIAL AGEING	520-545 °C	4-10 hours	20-50 °C	135-160 °C	2-7 hours
T7 HYPERAGEING	480-530 °C	1-8 hours	20 °C	190-240 °C	1-8 hours

The temperatures and the duration of the treatments vary according to the type of alloy, melting (shell, sand or die casting) and the result you want to obtain.

Ideal parameters shall be determined by a test.

EQUIVALENTS OR SIMILARS FOREIGN REGULATIONS

	ITALY	GERMANY	FRANCE	G.B.R.	USA	ISO	JAPAN	TURKEY
Equivalents	UNI	Din1725/5-86	NFA57-105	BS1490-88	ASTM 179-82	3522-84	JIS H2211-92	ETIAL
Similar	5080	DIN 349	A G 10 S	LM 10	518.1			

What is indicated in this data sheet is limited to inform only and does not imply any guarantee regarding the properties reported.

Everything that involves decisions based on the information stated here is direct responsibility of the end user, as well as any risks, not excluded from the verification.